REPORT DOCUMENTATION PAGE

Form Approved OMB NO. 0704-0188

and maintaining the data needed, and complet	information is estimated to average 1 hour per reting and reviewing the collection of information.	Send comment regarding	this burden estimates or a	any other aspect of this collection of	
information, including suggestions for reducit	ng this burden, to Washington Headquarters Serv	rices, Directorate for infor	mation Operations and Re	ports, 1215 Jefferson Davis Highway, Suite	
1204, Arlington, VA 22202-4302, and to the	Office of Management and Budget, Paperwork R	eduction Project (0704-0)	188,) Washington, DC 205	ND DATES COVERED	
1. AGENCY USE ONLY (Leave Blank	k) 2. REPORT DATE	15 October 2001	Final 4/20/00 – 4/		
			111101 4/20/00 4/	, 10,01	
4. TITLE AND SUBTITLE			5. FUNDING NUME	BERS	
Hall & Seebeck Measurement System			DAAD 19-00-1-01	49	
For Evaluation of Alloy Phase S	tability Microstructure & Properties				
6. AUTHOR(S)					
David L. Olson					
Timothy R. Ohno			8. PERFORMING O	RGANIZATION	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Dept of Metallurgical and Materials Engineering				ER MT-CWJCR-001-020	
Colorado School of Mines			ida okt kombi	577.557.557.525	
Golden CO 80401-1887					
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES)			10. SPONSORING /	MONITORING	
7. bi ondonation institutional to the action of the action			AGENCY REPORT NUMBER		
U. S. Army Research Office			P-40863-MS-RIP	•	
P.O. Box 12211			• 1		
Research Triangle Park, N	C 27709-2211	İ			
Tesomen Trangle Lara, 14	027.07.221				
11. SUPPLEMENTARY NOTES					
The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official					
Department of the Army position, policy or decision, unless so designated by other documentation.					
Department of the Famy position	, poney or con sisting and an ex-				
12 a. DISTRIBUTION / AVAILABILE	TY STATEMENT		12 b. DISTRIBUTIO	N CODE	
Approved for public release;	distribution unlimited.				
12 ADOTT ACT (Marine 200 marks)					
13. ABSTRACT (Maximum 200 words)					
Hall and Seebeck measurement systems have been specified, purchased, facilitated and calibrated. These					
aveterns are assisting in res	search efforts to develop new	analytical ann	roaches based	on electronic tools which	
systems are assisting in les	earch enorts to develop new	anarytical app	roactics, based		
	industry well, to assess struc				
These electronic systems v	vill develop multiple measure	ements techniq	ues to assess all	loy phase stability, aging,	
microstructure and properties. Seebeck coefficient measurements have already been correlated with the					
diffusible hydrogen content in alloy with high transition metal element contents. These results show promise for					
assessment of hydrogen effects in gun barrel steel, naval nickel aluminum bronze fasteners, and high strength					
steel welds. Hall and Seebeck measurements have been used to characterize the microstructure in alloy thin					
films. Research is in progress to develop electronic techniques to determine the susceptibility of sigma					
formation in superalloys. These electronic techniques will offer rapid non destructive microstructural					
assessment with quantitative data acquisition for easy long term storage of product quality assurance.					
assessment with quantitudive data acquisition for easy fong term storage of product quarty assurance.					
			.: 'a		
	-				
14. SUBJECT TERMS		ort 1 3 2001		15. NUMBER OF PAGES	
				5	
// // // ···			i	14 PRICE CORE	
$\mathcal{H}_{\mathcal{L}_{\mathcal{L}_{\mathcal{L}}}}$				16. PRICE CODE	
17. SECURITY CLASSIFICATION	18. SECURITY CLASSIFICATION	19. SECURITY CI	ASSIFICATION	20. LIMITATION OF ABSTRACT	
OR REPORT	ON THIS PAGE	OF ABSTRAC	Γ		
UNCLASSIFIED	UNCLASSIFIED	UNCLA	SSIFIED	UL Standard Form 208 (Par 2 90)	
NSN 7540-01-280-5500				Standard Form 298 (Rev.2-89)	

MASTER COPY: PLEASE KEEP THIS "MEMORANDUM OF TRANSMITTAL" BLANK FOR REPRODUCTION PURPOSES. WHEN REPORTS ARE GENERATED UNDER THE ARO SPONSORSHIP, FORWARD A COMPLETED COPY OF THIS FORM WITH EACH REPORT SHIPMENT TO THE ARO. THIS WILL ASSURE PROPER IDENTIFICATION. NOT TO BE USED FOR INTERIM PROGRESS REPORTS; SEE PAGE 2 FOR INTERIM PROGRESS REPORT INSTRUCTIONS.

MEMORANDUM OF TRANSMITTAL

U.S. Army Research Office ATTN: AMSRL-RO-BI (TR) P.O. Box 12211 Research Triangle Park, NC 27709-2211

Reprint (Orig + 2 copies)	☐ Technical Report (Orig + 2 copies)			
Manuscript (1 copy)	Final Progress Report (Orig + 2 copies)			
	Related Materials, Abstracts, Theses (1 copy)			
CONTRACT/GRANT NUMBER: DAAD 19-00-1-0149				
REPORT TITLE: Hall & Seebeck Measurement System For Evaluation of Alloy Phase Stability Microstructure & Properties				
is forwarded for your information.				
SUBMITTED FOR PUBLICATION TO (appl	licable only if report is manuscript):			

Sincerely,

Dant Ohm

David L. Olson 34040MS
Dept of Materials Science
Colorado School of Mines
Golden CO 80401-1890

Project Title: Hall and Seebeck Measurement System for the Evaluation of Alloy Phase Stability, Microstructure and Properties

Contract Number: DAAD 19-00-1-0149

FINAL REPORT

Submitted to:

United States Army Research Office
Materials Science Division
% Dr. William M. Mullins
4300 South Miami Boulevard
P. O. Box 12211
Research Triangle Park, North Carolina 17709-2211

Submitted by:

Dr. David L. Olson Principal Investigator J. H. Moore Dist. Professor Dept. of Met. and Mat. Eng. 303-273-3955 Dr. Timothy R. Ohno Co-Principal Investigator Associate Professor Dept. of Physics 303-273-3847

Colorado School of Mines Golden, Colorado 80401

Introduction

The use of electronic and magnetic analytical instrumentation to assess structure-property relationships as they relate to needs of the electronic industry has made it possible to produce high quality and reproducible devices. The ability to make property determination and quality control has made it possible. There have been significant advancements in these electronic and magnetic instrumentation as seen by their measurement sensitivity, reduction in instrument size, electronic controls and data acquisition and most important a sound fundamental understanding the correlation of the measurement with electronic and phase structure. Opportunities are now arising for the use of these established analytical instruments and techniques for phase and microstructure determination, phase stability and prediction of service life of structural materials, such as found in high performance engines, vehicles and weapon systems. The advent of non destructive evaluation of microstructure and properties is offering significant savings in both money and time in maintaining many defense systems.

The project was to purchase the electronic analytical systems for use as both for electronic property characterization and for the development of practices to assess microstructure, phase determination, phase stability and the prediction of remaining service life of structural component. The instruments purchased, which will be used with the existing comprehensive optical and electronic microscopy, x-ray diffraction and surface analytical systems at the Colorado School of Mines, are listed below:

DURIP Equipment Summary

The equipment purchased is consistent with the proposed instruments described in the proposal.

1. Hall Measurement System

Manufacturer: Lake Shore Cryotronics, Inc., 64 E. Walnut St., Westerville, Ohio, 43081-2399; Fax: (614) 891-1392; Telephone: (614) 891-1392

1. 7507 Low Voltage Autoswitching, High Sensitivity Hall measurement system with sample holder and cards for samples from 1 ohm to 150 gigaohm and in a

temperature range from 77 K to 400 K. High output magnet power supply and Neslab CFT-300 recirculating chiller

2. 75014 Closed Cycle Refrigerator Sample Module with a compressor, rated for a temperature range between 15 K and 350K.

Total cost of system: \$179,953.

2. Seebeck Measurement System

Manufacturer: MMR Technologies, Inc. (1400 North Shoreline Boulevard, Suite A-5, Mountain View, CA 94043-1346; Fax: (650) 9629647; Telephone: (650) 962-9620

 Seebeck Effect Measurement System, the model K20SB100-5R includes K-20 Programmable Temperature Controller with control software, two Extended Wide Temperature Range Thermal Stage Units, SB100 Seebeck Electronics and software (no computer)

2. Hardware for vacuum and pressure manifolds and control, computer interface (from assorted vendors), required for custom pumping arrangement.

Total cost of system: \$22,440

Both systems, which are permanently installed at CSM in Meyer Hall, have been tested, calibrated and are fully functional. The initial measurements on a wide variety of samples have shown promising results. For instance measurements on TiB_x - TiC and $CrSi_x$ thin films show low Hall mobility but very high carrier concentration ($\sim 10^{23}$ cm⁻³) for samples of low resistivity. In addition measurements on highly resistive, undoped CdTe and CdS thin films as well, have been made to demonstrate the full range of the system.

Our ability to measure conductive metal films with the Hall measurement system has also been performed and has demonstrated that it can produce high quality results that are very useful for our current and proposed studies in the development of advanced alloys based on electronic based alloy theories. The measurement of the hydrogen content in materials using the Seebeck measurement system is becoming an every day practice. Projects for which this equipment will be used are listed below. The project numbers indicate investigations that are currently funded by DoD.

1. PHACOMP Meter - Sigma Phase in Turbine Engines

New PHACOMP, the electron-based calculation technique, has been used to investigate nickel-based weldments. These calculations are important for predicting the tendency of austenitic alloys to precipitate topologically close-packed phases which adversely affect mechanical and corrosion properties. Since Phacomp and New Phacomp computations are based on the electronic filling of the d-band, Seebeck coefficient measurements should offer a direct measurement practice to determine the tendency of having a phase change in the these alloys. This new

electronic characterization capability allows for the development of direct nondestructive evaluation of the phase stability of parts in service, such as turbine blades. (ARO DAAD 19-01-1-0375)

2. Advanced Hydrogen Sensor for Materials

Both diffusible and trapped hydrogen contents are being measured in hydrogen storage materials and structural alloys. Seebeck measurements have been found to offer a rapid assessment of the hydrogen contents in alloys with substantial transition element contents. Techniques are been developed for steel weldments and gun barrel steel under ARO contract and an initial effort is under way to assess the hydrogen content in aluminum bronze fasteners, which were hydrogen charged by cathodic protection, for the U. S. Navy.

(Steel weldments; ARO DAAD 19-00-1-0149, barrel steel for Benet Arsenal, Marine fastners: U. S. NSWC).

3. Characterizing Thin Film Microstructure

The new equipment is being used to characterize thin film microstructure to develop predictive models for evolution of thin film microstructure and properties. These measurements will form an integral part of the graduate education for physics, metallurgy and materials science, as well as supporting research activities in the CSM Advanced Coating and Surface Engineering Laboratory.

4. Colloboration with Los Alamos National Laboratory

New NDE techniques for evaluating the metallurgical aging of plutonium alloys. The current project makes plutonium measurements at LANL, but surrogate materials have been measured with the Seebeck measurement system at CSM to assist in designing the LANL equipment..

5. Collaboration with U.S. Naval Surface Warfare Center NDE R and D Group The equipment will be used in collaboration with Robert Denale (Head, Welding and NDE R&D U.S. Naval Surface Warfare Center) to measure diffusible hydrogen associated with welding of high strength steels. The high strength steel weld metal program is being performed by other investigators under ONR Grant N00014-94-1-0694.

6. Collaboration with Army Laboratory

We have had discussions with U.S. Army Benet Laboratory in the use of advanced methods to measure hydrogen content in steels in gun barrels. Our new instrumentation will allow preliminary NDE studies with the guidance of Paul Cote (Benet Laboratory).

7. Measurement of properties of transparent conducting oxide coatings

Transparent conducting oxide coatings form an important part of display technologies, photovoltaics and window coatings. Rapid electrical characterization with Hall and Seebeck will be used to characterize and develop materials with superior properties.

8. Studies of semiconductor thin films for photovoltaic applications

The processing stages of photovoltaic modules have great impact on solar cell efficiency and stability. The cell properties will be correlated with measurements on both cells and sub-modules consisting of layers of the actual devices. This work is supported by DOE through its Thin Film Partnership.

ACKNOWLEDGEMENTS:

The numerous investigators, who will be frequently using these instruments to further their work, will acknowledge the support of the DOD Equipment grant program.